

HEAD OFFICE

17 Tapgeol-gil Ungchon-myeon Ulju-gun Ulsan Korea Tel.82-52-228-7500 Fax.82-52-268-5578

OVERSEAS DIRECT

Tel.82-52-228-7563 Fax.82-52-228-7530 **SEOUL OFFICE**

Tel.82-2-2635-1380 Fax.82-2-2635-1382

KUKIL INNTOT is a professional manufacturer of gasket, packing coupling with the latest technology not only for the plant but also the plant maintenance and emergency repair.

NON-ASBESTOS GASKET

Type ' KN 10 '

Product Reference:

K/# KN 10

Description:

The main components are Carbon Fibers with SBR binder to form non-asbestos

joint sheet gasket.


KUKIL KN10 gasket are used for Saturated steam, water and inert gases.

Benefits: Heat & Pressure Resistance, Easy to Handle and Cut.

Service:

Maximum recommended Temperature : 340° C Maximum recommended Pressure : $140 \text{ kg}_f/\text{cm}^2$

Typical Specifications:



TYPICAL MATERIAL PROPERTIES			
Test Method	Descripiton	Specified Value	
ASTM D792	Density	1.6~1.8g/cm³	
ASTM F152	Tensile Strength > 7Mpa		
ASTM F36	Compressibility	5~15%	
	Recovery	> 55%	
ASTM F37	Sealability		
	- ASTM Fuel A	< 1ml/hr	
	- Nitogen	< 1ml/hr	
ASTM F38	Creep Relaxation	< 20%	
DIN 3535	Gas Permeability	< 0.03cc/min	

Gasket Design Data: standard ASME Section ™ Div.1

Thickness	Gasket Factor " m "	Min. Design Sealing Stress " y "
1.5t, 2.0t	2.75	3,700 psi
3.0t	2	1,600 psi

Availability:

Gasket Size: Max. 1500mm (Non-seam)

Max. 5000mm (seam)

Thickness: 1.5mm, 2.0mm, 3.0mm, etc.

Remark:

- The specification of product is written by manufacturer, and it is changed frequently.
- The recommended flange surface finish for INNOSILD KN 10 gasket is from 125~500AARH